

Caratteristiche raccomandate acqua
Recommended water characteristics
Caractéristiques de l'eau recommandées
Minimale Wassereigenschaften

Proprietà Property Propriété Eigenschaft	300 gr/m ² Galvanized steel Tôle en acier zingué Verzinkter Stahl	AISI 304 Stainless Steel Acier Inoxydable Edelstahl	AISI 316 Stainless steel Acier Inoxydable Edelstahl
pH pH pH pH-Wert	7,0 – 9	6,0 – 9,5	6,0 – 9,5
Solidi totali in sospensione (ppm) Total suspended solids (ppm) Solides totales en suspension (ppm) Suspenderter Festanteil, Gesamt (ppm)	< 25	< 25	< 25
Conduttività (micro-Siemens/cm) Conducivity (micro-Siemens/cm) Conductivité (micro-Siemens/cm) Leitfähigkeit (micro-Siemens/cm)	< 2.400	< 4.000	< 5.000
Alcalinità CaCO ₃ (ppm) Alcalinity CaCO ₃ (ppm) Alcalinité CaCO ₃ (ppm) Alkalinität CaCO ₃ (ppm)	75 – 600	< 600	< 600
Durezza CaCO ₃ (ppm) Hardness CaCO ₃ (ppm) Dureté CaCO ₃ (ppm) Härte CaCO ₃ (ppm)	50 – 750	< 600	< 600
Silice SiO ₂ (ppm) Silica SiO ₂ (ppm) Silice SiO ₂ (ppm) Silizium SiO ₂ (ppm)	< 150	< 150	< 150
Cloruri Cl ⁻ (ppm) Chlorides Cl ⁻ (ppm) Chlorures Cl ⁻ (ppm) Chloride Cl ⁻ (ppm)	< 400	< 400	< 2.000
Carica Batterica totale (cfu/ml) Bacterial (cfu/ml) Charge totale bactérienne (cfu/ml) Keimbelastung, Gesamt (cfu/ml)	< 10.000	< 10.000	< 10.000

W-Tech S.r.l.

Via Cartiera 90/A- 40037 Sasso Marconi- (BO) Italy

T: +39 051 6783010 F: +39 051 6784941

info@w-tech.it- www.w-tech.it

Reg. Imp. BO C/F- P.Iva/VAT : IT03079111203- Rea BO 490312- Cap. Soc. 32.000€ i.v.

